



AXON PRODUCTS

307 ECHELON ROAD • GREENVILLE, SC 29605
TEL. 864-299-2819 • FAX 864-299-2820
EMAIL info@axonproducts.com

WOOD TECHNICAL DATA

PSP-930 VERTICAL SPRAY SEALER

Revised: October 2007

This clear, sprayable, polyester sealer provides excellent build and filling properties. It is characterized by its high thixotropic index, which provides excellent hang for vertical spray applications. It also provides excellent sand ability. This sealer meets or exceeds all existing emission control regulations. This sealer should be used on product that will be used indoors and should not be applied to products that are exposed to freezing temperature for a prolonged period of time as blushing can occur.

GENERAL RULES:

1. This product should be stored no longer than 6 months from date of manufacture. It should be kept in its original container in a dark, cool, dry place away from a source of heat and at a temperature below 86°F.
2. For best performance the temperature of the product and the room should be 69 - 79°F and the relative humidity 35 - 75%.
3. The substrate needs to be well sanded with 180 - 220 grit paper, and must be free from dust and grease. The moisture content of the substrate should vary from 8 - 12%.
4. An ISC/ISB Series insulator must be applied before coating with polyester on woods such as Teak, Rosewood, and other exotic woods with a high content of tannin. It also must be applied after staining.

MIXING INSTRUCTIONS:

The PSP-930 Vertical Spray Sealer requires the user to add both promoter and catalyst just prior to use. The standard additions are as follows:

- A) Promoter: Add 1-2% by volume of PSC-507 Polyester Promoter. This mixture will be stable approximately 12 hours without a noticeable rise in viscosity.
- B) Catalyst: Add 2% or 4% by volume. There are two catalysts offered. Which one to use depends on the spray equipment to be used? They are as follows:
1. Use 2% of **PCC-901** when two-component pumps are available. This catalyst provides minimal dry times and becomes dust free in approximately 20 - 30 minutes. Once catalyzed, however, the usable pot life is approximately 15 minutes (temperature dependant). Therefore it is necessary to use two-component equipment or to spray only an amount that can be consumed in this time frame.
 2. Use 4% of **PSC-904** when a pressure pot or cup gun is to be used. This catalyst will be two times the pot life of PCC-901. The dust free time, however, is extended to 1½ hour.

PSP-930 VERTICAL SPRAY SEALER

Page 2

ATTENTION:	DO NOT MIX CONCENTRATED PSC-507 PROMOTER AND PCC-901 CATALYST TOGETHER. THIS MIXTURE CAN RESULT IN A VIOLENT CHEMICAL REACTION!
-------------------	--

		<u>5 Gallon Mix</u>	<u>1 Gallon Mix</u>	<u>1-Quart Mix</u>
PSP-930	Vertical Spray Sealer	20,000 ml	4,000 ml	1,000 ml
PSC-507	Polyester Promoter			
	Use a 1.0% mix	200 ml	40 ml	8 ml
PCC-901	Polyester Catalyst 2.0% or			
PSC-904	Polyester Catalyst L.P.			
	Always use a 4.0% mix		16 ml	

REDUCTION - VISCOSITY:

Usually a reduction of approximately 5% by volume will provide a satisfactory spray viscosity. If ambient temperature is below 80°F (27°C), reduce with RED-912 Solvent / Reducer. During very warm summer months when ambient temperatures exceed 80°F, reduce with RED-937 Solvent / Reducer. We do not recommend spraying polyesters when ambient conditions are over 95°F (35°C) or the relative humidity above 75%, because the dry time and gel time become too fast which can cause "solvent pop" and other surface problems.

SPRAYING:

Most spray equipment can be used*. It is important that the sealer be applied as "wet" as possible without sagging (approximately 6 - 8 mils gives best results). Keep air pressure low, i.e. 30 - 45 psi at the gun. Avoid dry spraying. Unlike lacquers, polyesters do not have enough solvent to completely re-wet dry spray.

If two or more coats are desired, wait approximately 15 minutes or until "tacky" before spraying the second coat. If subsequent coats are desired after the polyester is dry, the part should be well sanded with 320-grit sandpaper to prevent intercoat adhesion problems.

Because we cannot anticipate or control the many different conditions which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information of the suitability or our products in any given situation. Users of our products should make their own tests to determine the suitability of each such product for their particular purposes. The products discussed are sold without such warranty, either express or implied. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. All chemicals may present unknown health hazards and should be used with caution. Although certain hazards are described in this publication, we cannot guarantee that these are the only hazards which exist. Users of any chemical should satisfy themselves by independent investigation of current scientific and medical knowledge that the material can be used safely.

PSP-930
VERTICAL SPRAY SEALER

Page 3

*** Recommended Spray Equipment:**

Graco 700N	Conventional spray gun 2.5 mm #3 tip and needle, #3 air cap
DeVilbis JGHV530	HVLP spray gun (pressure feed) FF tip and needle, #705 air cap

DRY TIME:

A) With PCC-901 Polyester Catalyst:

Dust Free	30 - 45 minutes
Print Free	60 - 75 minutes
Dry Hard	3 - 4 hours
Full Cure	5 - 7 days

B) With PSC-904 Polyester Catalyst L.P.:

Dust Free	80 - 100 minutes
Print Free	1½ - 2 hours
Dry Hard	6 - 8 hours
Full Cure	5 - 7 days

Note: Ambient temperature has a significant impact on dry times. For example, subjecting the part to 15 minutes of warm moving air after 15 minutes of flash time at 100°F will reduce the print free time by 50 - 75%. Conversely, it is important to note that the chemical reaction during curing will stop at temperatures below 68°F (20°C) or a relative humidity below 35%. Parts permitted to dry overnight must be subjected to a temperature above 68°F.